


PREVIEW OF RESULTS

Client: DYNAMOBEL
Date of test: 8th of January, 2016
Complete results are available to the client



Test carried out by
 LGAI Technological Center S.A.

Measurement of airborne sound insulation according to EN ISO 10140-2



Frequency Hz	R
100	31,0
125	29,8
160	33,5
200	34,4
250	37,1
315	35,8
400	38,6
500	39,1
630	43,5
800	47,0
1000	48,5
1250	49,3
1600	50,2
2000	50,8
2500	52,0
3150	53,8
4000	61,8
5000	67,1

Test element description:

LINE CRYSTAL 2 GLASSES PARTITION

Glazed internal partition composed of double laminated glass pane 6+6 Silence and aluminium profiles framing system.



WEIGHTED SOUND REDUCTION INDEX, R_w (C; C_{tr})

46 (-2; -5) dB